

Prep and Spill Control Pads

PP Delnet Netting / Airlaid Wood Pulp and Binder / PE Film

Tested according to IEST-RP-CC004.3 standards

Cleanroom Level Recommendation*

ISO 3 4 5 6 7 8

Property	Typical Value
Basis Weight	155 gsm
Total Absorbency	790% (12.25 g / 1.55 g)
Total Absorption	SPAF: 11" x 16" (28 x 40.5 cm) - 139 g of water SPFM: 16" x 22" (40.5 x 56 cm) - 278 g of water
Elmendor Tear	MD 377 g TD 160 g
Tensile Yield	MD 6.44 lbs (2.92 kg) TD 6.03 lbs (2.74 kg)
Tensile Break	MD 3.61 lbs (1.64 kg) TD 4.81 lbs (2.18 kg)
Elongation	MD 745% TD 155%

Notes

1. Data shown are typical values and should not be used as product specifications.
2. Total absorbency percentage is weight of water absorbed divided by sample weight.
3. Valid product comparisons may only be obtained through side-by-side testing in the same test facility, under similar conditions. Current and/or comparison data may be available. Please contact an FG Clean Wipes representative for details.
4. FG Clean Wipes makes general recommendations on which wipers are suitable for different cleanroom classifications. However, specific applications may affect that recommendation. The final decision should be made by the end user for their particular application.

* The above recommendations are based on typical industry wide applications based on general cleanroom cleanliness classifications. Please consult our experienced FG Clean Wipes sales representatives for specific cleanroom product selections for critical and/or specialized applications based on a wider range of selection criteria.

